



Technical Data Sheet

Clear Thermal Anti-fog Greenhouse Film

Product Specifications

Thickness	From 100 to 200 microns			
Width	Up to 14 m			
Length	Per client requirements			
Seasons No.	1, 2 or 3 seasons depending on UV-Stabilizer type percentage, film,thickness and area total radiation			

Mechanical & Optical Properties

Optical Properties		Test method	Unit	Value
Light Transmission		ASTM D 1003	%	90
Light Diffusion		ASTM D 1003	%	> 35
Thermicity Effect		ASTM D 1003	%	> 75
Mechincal Properties		Test method	Unit	Value
Tonsilo Strongth	MD	Tensile Strength	МРа	28
Tensile Strength	TD			25
Elongation	MD	Elongation	%	500
Liongation	TD			650

Note:

The above information obtained from analysis performed in our labs and was based on reliable and standard laboratory testing procedures. The information contained herein is to be used only as guide for using our film. SHOUMAN does not offer any guarantee on the results and does not accept any liability arising out of the use of the information contained herein.

www.shouman.com

8 El Gaish Stree Mansoura - Egyp info@shouman.com www.shouman.com +2.050.2.300.200 +2.050.2.300.600